




CEWELD AA M610

TYPE	Seamless metal-powder cored wire without slag for M21									
ANWENDUNGEN	Steel construction, shipbuilding, pressure vessels, mechanical engineering, pipe work, offshore, crane building, heavy transport, lifting equipment respecting the NACE requirements.									
EIGENSCHAFTEN	Seamless metal cored wire with remarkable stable arc and no spatters. Excelent for use in automated welding applications such as orbital Mag or robotic welding.This wire offers a unique covering range that anables you to use only one wire to cover more procedures upto 620N/mm2 yield strenght steels. AA M610 can also be used for constructions that needs post weld heat treatment after welding and still offers excellent impact properties. Due to the seamless production process the hydrogen content is below 3ml/100gr weld metal even after long storage.									
KLASSIFIKATION	AWS	A 5.28: E100C-K3 H4								
	EN ISO	18276-A: T 62 6 Mn1NiMo M M21 1 H5								
	F-nr	6								
	FM	2								
GEEIGNET FÜR	Reh < 6200 MPa Iso 15608: ~3.2 (460 < Reh ≤ 690 MPa) S620Q, S620QL, S620QL1-S620QL1, 20MnCr65, 28CrMn43 L480 - L550, X65, X80, X90 ASTM A 514 Gr. F, H, Q; A 709 Gr. 100 Type B, E, F, H, Q; A 709 Gr. HPS 100W Weldox 600, Dillimax, S690QL1, Hardox, Naxtra 63, Naxtra 70, Optim 600 mc plus, Weldox 500, Hardox, Domex 460 MC, Domex 500 MC, Domex 550 MC, Domex 600 MC, Domex 650 MC, Domex 600 MC, Hardox 400, XAR 400, Dillidur 400, Oceanfit 100, Oceanfit 600, alform plate 620 M, aldur 620 Q, 620 QL, 620 QL1,									
ZULASSUNGEN										
SCHWEISSPOSITIONEN										
TYPISCHE CHEMISCHE ANALYSE DES SCHWEISSMETALLS (%)	C	Si	Mn	P	S	Cr	Ni	Mo	V	Cu
	0.06	0.6	1.7	0.007	0.014	0.03	0.93	0.46	0.001	0.07
MECHANISCHE GÜTEWERTE	Heat Treatment			R _{p0,2} (MPa)	R _m (MPa)		A5 (%)	Hardness		
	As Welded			634	711		25	HRc		
RÜCKTROCKNUNG	Not required									
GAS ACC. EN ISO 14175	M21									



CEWELD AA M610

AA M610 1,2MM

Packaging	KG/unit	EanCode
K-300	16	8720663423443