




CEWELD FL 160

TYPE	High basic SAW flux with low hydrogen content.		
ANWENDUNGEN	Boiler works, vessel and structural steel works, tanks and pressure vessels, offshore lifting applications, platforms etc..		
EIGENSCHAFTEN	FL 160 is a highly basic SAW flux with low hydrogen content. Basicity: about 3 (according to Boniszewski) Current: DC or AC, in single or multi-wires Grain size: 2-20		
KLASSIFIKATION	EN ISO	14174: SA FB 1 55 AC H5	
GEEIGNET FÜR	S355, S420, S460, X65, X70, X80		

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPISCHE CHEMISCHE ZUSAMMENSETZUNG NACH GEWICHT (%)

Al ₂ O ₃	CaF ₂	SiO ₂	CaO+MgO
20	20	15	40

MECHANISCHE GÜTEWERTE

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175



CEWELD FL 160

FL 160 0,2 - 2,0MM

Packaging	KG/unit	EanCode
Bag	25	8720663404008
Bag	25	8720663404015