

# CEWELD SA 430

**TYPE** Solid wire for submerged arc welding with 17% Cr.

**ANWENDUNGEN** Cladding seats, valves, wheels, shafts etc.

**EIGENSCHAFTEN** Submerged arc welding wire to be used with fused flux FL 880 or agglomerated flux FL 838 flux with excellent welding properties. Stainless deposit with low carbon content. Low heat input is recommended to avoid pronounced grain coarsening. Absence of stabilization means that this steel is distinctly vulnerable to sensitization phenomenon during welding, even though martensite hogs a great amount of carbon and nitrogen.

**KLASSIFIKATION**

AWS	A 5.9: ER430
EN ISO	14343-A: S 17
W.Nr.	1.4016
F-nr	6
FM	5

**GEEIGNET FÜR** 1.4000, 1.4002, 1.4016, 1.4057, 1.4113, 1.4057, 1.4059, 1.4332, 1.4502, 1.4509, 1.4510, 1.4511, 1.4512, 1.4520, 1.4523, 1.4712, 1.4713, 1.4724, 1.4740, 1.4741, 1.4742, 1.4842, X7Cr14, X12Cr13, X17CrNi16-2, X6Cr13, X6CrAl13, X6Cr17, X17CrNi16-2, X2CrTiNb18, X3CrTi17, X3CrNb17, X2CrTi12, X2CrTi17, X10CrSi6, X10CrAlSi7, X10CrAlSi13, X10CrAlSi18  
UNS S40300, S40500, S40900, S41000, S42900, S43000, S43035, S43036, S43100, S44200  
AISI 403, 405, 409, 410, 429, 430, 430Cb, 430Ti, 439, 431, 442

**ZULASSUNGEN**

**SCHWEISSPOSITIONEN**



**TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)**


C	Si	Mn	P	S	Cr	Ni	Mo
0.02	0.4	0.46	0.02	0.01	17	0.3	0.3

**MECHANISCHE GÜTEWERTE**

Heat Treatment	R <sub>p0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness
As Welded	>300	>450	>20	250 HB

**RÜCKTROCKNUNG** Not required

**GAS ACC. EN ISO 14175**



# CEWELD SA 430

SA 430 3,2MM

Packaging	KG/unit	EanCode
K-415	25	8720663412072