


CEWELD Alloy X

TYPE	Nickel based filler metal for welding similar NiCrMo alloys									
ANWENDUNGEN	Suitable for joining and cladding Nickel alloys, stainless steel, carbon steel and low alloyed steels. UNS: N06002									
EIGENSCHAFTEN	CEWELD Alloy X is a nickel- chromium-iron-molybdenum alloy that possesses an exceptional combination of oxidation resistance, fabricability and high-temperature strength. It has also been found to be exceptionally resistant to stress-corrosion cracking in petrochemical applications. CEWELD Alloy X exhibits good ductility after prolonged exposure at temperatures of 1200, 1400, 1600F (650, 760 and 870°C) for 16,000 hours.									
KLASSIFIKATION	AWS	A 5.14: ERNiCrMo-2								
	EN ISO	18274: S Ni 6002(NiCr21Fe18Mo9)								
	W.Nr.	2.4665								
	F-nr	43								
	FM	6								
GEEIGNET FÜR	2.4665									
	UNS: N06002									
	Alloy HX, X, AMS 5754, AMS 5798, ASTM B619, Nickel alloys, stainless steel, carbon steel and low alloyed steels.									
ZULASSUNGEN										
SCHWEISSPOSITIONEN										
TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)	C	Si	Mn	Cr	Ni	Mo	Fe	W	Co	Cu
	0.1	0.8	0.9	22	50	9	19	0.8	2	0.4
MECHANISCHE GÜTEWERTE	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V				Hardness	
					RT					
	As Welded		660	30	100				HRc	
RÜCKTROCKNUNG	Not required									
GAS ACC. EN ISO 14175	I1									



CEWELD Alloy X

ALLOY X 1,14MM

Packaging	KG/unit	EanCode
BS-300	13,6	8720663420305