

CEWELD S-SnAg5

TYPE	6% silver containing cadmium free soft solder alloy
ANWENDUNGEN	- Copper pipe installation - Refrigeration and air-conditioning technology - Soft soldering of stainless steel - Also suitable for extreme cryogenic temperatures even up to -196 °C
EIGENSCHAFTEN	Alloy: Sn94Ag6 / Solidus: 221°C / Liquidus: 279°C / Deposit color: Silver / Shear Strength (copper lap joint): 10,600 PSI

KLASSIFIKATION

GEEIGNET FÜR	Copper, stainless steel
--------------	-------------------------

ZULASSUNGEN

SCHWEISSPOSITIONEN



MECHANISCHE GÜTEWERTE

RÜCKTROCKNUNG	Not required
---------------	--------------

GAS ACC. EN ISO 14175