




CEWELD 4850 Kb

TYPE	Basic electrode for heat resistant stainless steel SMAW welding
APPLICATIONS	CEWELD [®] 4850 Kb for repair and build-up welding of same and similar types of heat-resistant steels and cast steels.
PROPERTIES	CEWELD [®] 4850 Kb has high corrosion resistance and excellent weldability for both AC and DC+. The weld metal can be used up to 1050 °C in carburized and low-sulphur environments.
CLASSIFICATION	EN ISO 3581-A: E Z 21 33 Nb B 32 W.Nr. ~1.4850 FM 5
SUITABLE FOR	1.4876, 1.4861, 1.4859, 1.4958, 1.4959, G-X10NiCrNb 32 20, X10NiCrAlTi 32 20, X5NiCrAlTi 31 20, X8NiCrAlTi 31 21, UNS N 08800, N 08810, N 08811, Alloy 800H

APPROVALS CE

WELDING POSITIONS



TYPICAL CHEMICAL
ANALYSIS OF WELD METAL
(%)

C	Si	Mn	P	S	Cr	Ni
0.15	0.5	4.5	0.02	0.01	22	34

MECHANICAL PROPERTIES

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness
				RT	
As Welded	380	600	25	50	HRC

REDRYING 300°C / 2 hr

GAS ACC. EN ISO 14175



CEWELD 4850 Kb

4850 KB 2,5 X 350MM

Packaging	KG/unit	EanCode
Can	2,8	8720663415813