



CEWELD 327

TYPE	Solid stainless steel welding wire for high temperature applications					
APPLICATIONS	CEWELD® 327 is a high-alloy solid wire suitable for production and repair welding on similar or similar corrosion- and heat-resistant steels and steel castings. For furnaces that require improved resistance to reducing and oxidizing sulfur-containing gases, as well as for welding welded joints. Resistant to spalling up to 1100 °C.					
PROPERTIES	CEWELD® 327 produces a weld metal with 25% chromium and 4% nickel for build-up welding and joining components that must be corrosion, heat, and wear resistant. It is characterized by excellent weld quality and X-ray resistance, has a stable arc at high currents, and a coating that is easy to machine.					
CLASSIFICATION	EN ISO	14343-A: G 25 4				
	W.Nr.	1.4820				
	F-nr	6				
	FM	5				
SUITABLE FOR	1.4710, 1.4745, 1.4712, 1.4762, 1.4713, 1.4773, 1.4722, 1.4776, 1.4724, 1.4820, 1.4729, 1.4821, 1.4740, 1.4822, 1.4742, 1.4823 G-X30CrSi6, G-X40CrSi23 TP433, X10CrSi6 502, X10CrAl24 TP443, X10CrAl7 502, X8Cr30, X10CrSi13, G-X40CrSi29, X10CrAl13 TP405-CA15, G-X12CrSi 26 5, G-X40CrSi13, X20CrNiSi 25 4 TP329, G-X40CrSi17, G-X40CrNi 25 4 TP329, X10CrAl18 430B-TP430, G-X40CrNiSi 27 4 TP329HC AISI 327, ASTM A297HC					
APPROVALS	CE					
WELDING POSITIONS						
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Cr	Ni	
	0.1	0.6	2	26	5	
MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V -20°C	Hardness
	As Welded	450	660	15	50	HRc
REDRYING	Not required					
GAS ACC. EN ISO 14175	M11, M12					



CEWELD 327

327 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663415844

327 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663415851

327 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663415868