



CEWELD OA 58-66B

TYPE	High alloyed seamless flux cored wire for hardfacing against extreme abrasion.				
APPLICATIONS	Rebuilding wornout parts or protecting new machine parts to increase life that suffer from extreme abrasive wear				
PROPERTIES	High C-, Cr-, B-alloyed flux-cored wire electrode which forms extremely hard carbides for extremely hard deposits on parts subject to excessively heavy abrasive wear weldable with and without protective gas. Verry good wear resistance due to excellent first layer hardness properties. More than 1 or 2 layers should not be deposited. A Buffer layer with CEWELD® OA 4370 or CEWELD® OA MnCr is recommended in case of old layers or critical base metals. Weldable with M21 or without shielding gas.				
CLASSIFICATION	EN ISO	14700: T ZFe14			
SUITABLE FOR	58-66 HRc Hardfacing alloy used in mining, agriculture and steel mills, conveyor chains, agriculture, construction, mixer blades, paddles, cement pumps with excelent abrasion and wear resistance against sand and minerals				
APPROVALS					
WELDING POSITIONS	PAPBPCPF				
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	Cr	B
	2.6	0.6	0.9	17	0.9
MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
	As Welded				62 HRc
REDRYING	140°C / 24 hr				
GAS ACC. EN ISO 14175					