



CEWELD E 410 NiMo

TYPE

APPLICATIONS

PROPERTIES

CLASSIFICATION

SUITABLE FOR

APPROVALS

WELDING POSITIONS

TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

MECHANICAL PROPERTIES

REDRYING

GAS ACC. EN ISO 14175

Basic coated high performance electrode for surfacing and joint welding of ferritic-martensitic ferritic-martensitic chromium steels. (410NiMo, E 13 4)

CEWELD® E 410NiMo is used for welding similar martensitic and martensitic-ferritic steels in various applications such as water turbines, compressor construction, steam power plant construction, continuous casting rolls, centrifuges, valves, Pelton and Francis turbines. For thicker materials (over 10 mm), preheating to a maximum of 150°C is recommended, followed by tempering or normalizing after welding. When welding joints, a bufferlayer with CEWELD® CroNi 29/9 S or CEWELD® 4370 Ti electrode is often advised.

CEWELD® E 410NiMo has comparable properties to steels of the same or similar types. It is resistant to water and steam. The preheating and interpass temperature should be 100 - 160°C for thick-walled parts. The heat input should be max. 15 kJ/cm. Annealing at 580 - 620°C is possible.

AWS
EN ISO
F-nr
FM

A 5.4: E 410NiMo
3581-A: E 13 4 B 42
4
5

13%Cr - 4%Ni - 0,5%Mo Steel
1.4000, 1.4001, 1.4002, 1.4313, 1.4317, 1.4407, 1.4413, 1.4414,
GX4CrNi13-4, X3CrNiMo13-4, GX5CrNiMo13-4, GX4CrNiMo13-4, X 6 Cr 13, X 7 Cr 14, X 6 CrAl 13
ACI Gr. CA 6 NM

PA

PB

PC

PF

C	Si	Mn	Cr	Ni	Mo
0.055	0.77	0.65	13	4.1	0.6

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
605°C- 645°C 8h	600	800	25	310 HB

300°C / 2 hr



CEWELD E 410 NiMo

E 410 NIMO 2,5 X 350MM

Packaging	KG/unit	EanCode
Can	2,5	8720663411549

E 410 NIMO 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	2,5	8720663411556

E 410 NIMO 4,0 X 350MM

Packaging	KG/unit	EanCode
Can	2,5	8720663411563