

CEWELD Ni-Rod FM 99

TYPE Solid Nickel based filler metal for MIG welding.

APPLICATIONS CEWELD Ni 99 FM 99 is developed for welding ductile, grey and malleable cast irons. Ni 99 can also be used for dissimilar welding between cast iron and low alloyed steel or carbon steels.

PROPRIÉTÉS This Nickel weld deposit offers a easily machinable weld deposit with high ductility and no undercut.

CLASSIFICATION AWS A 5.15: E Ni-CI, 1071: SC Ni-CI
W.Nr. UNS N02215

CONVIENT POUR Grey cast iron, malleable, nodular, dissimilar welding : NF A 32-101 : FGL 150, 200, 250, 300, 350, 400. NF A 32-201 : FGS 370-17, 400-12, 500-7, 600-3, 700-2. NF A 32-702 : MN 350-10, 380-18, 450-6, 350-4, 650-3. DIN 1691 : CG-14, 18, 25, 30. DIN 1693 : GGG-40, 50, 60, 70. DIN 1692 : GTS-35, 45, 55, 65, 70.

AGRÉMENTS

POSITIONS DE SOUDAGE



ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)


C	Si	Mn	S	Ni	Fe	Cu
0.09	0.35	0.35	0.01	Rem.	0.4	0.2

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded	250	490	12	HRc

ETUVAGE Not required

GAS ACC. EN ISO 14175 M11



CEWELD Ni-Rod FM 99

NI-ROD FM 99 1,2MM

Packaging	KG/unit	EanCode
BS-300	13,6	8720663417688