




CEWELD AA R690

TYPE	Seamless micro-alloyed rutile flux-cored wire for high strength steels																						
APPLICATIONS	Shipbuilding, steel and vessel construction, mechanical engineering and pipe work, offshore, crane building, lifting, platforms. Steels with yield strength up to 690 MPa (100 ksi).																						
PROPRIÉTÉS	CEWELD® AA R690 was one of “The first seamless rutile FCW with extreme low hydrogen for S690” Excellent for use in positional welding where high deposition rate is required, suitable for temperatures down to -60 °C (with offshore Approval down to -40°C). Excellent for use on ceramic backing and Mag orbital welding in all positions. Extreme low spatter properties and excellent arc stability with fast freezing slag.																						
CLASSIFICATION	AWS A 5.29: E 111T1-GM-J H4, A 5.36: E111T1-M21A4-G-H4 EN ISO 18276-A: T 69 6 Z P M21 1 H5 F-nr 6 FM 2																						
CONVIENT POUR	Reh < 690 MPa Iso 15608: 2.2 u 3.2 (460 < Reh ≤ 690(700) MPa) 1.8914, 1.8927, 1.8931, 1.8928, 1.8974, 1.7147, 1.7149, 1.8734 S620Q, S620QL, S690Q, S690QL, S620QL1-S690QL1, 20MnCr65, 28CrMn4-3 L480 - L550, X65, X80, X90, X100 ASTM A 514 Gr. F, H, Q; A 709 Gr. 100 Type B, E, F, H, Q; A 709 Gr. HPS 100W Weldox 700, Dillimax 690, Hardox, Naxtra 63, Naxtra 70, Optim 700 mc plus, Weldox 500, Hardox, Domex 460 MC, Domex 500 MC, Domex 550 MC, Domex 600 MC, Domex 650 MC, Domex 700 MC, Hardox 400,Strenx 700; XAR 400, Dillidur 400, Oceanfit 100, Oceanfit 690, alform plate 620 M, 700 M, aldur 620 Q, 620 QL, 620 QL1, aldur 700 Q, 700 QL, 700 QL1, Salzgitter S700MC, Ympress Steel E690 TM, S700MC, Armstrong Ultra 650MC, 650 Mct, 700 MC.....																						
AGRÉMENTS	CE, Lloyds, DNV																						
POSITIONS DE SOUDAGE	      																						
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)	<table><tr><td>C</td><td>Si</td><td>Mn</td><td>P</td><td>S</td><td>Cr</td><td>Ni</td><td>Mo</td></tr><tr><td>0.06</td><td>0.4</td><td>1.6</td><td>0.015</td><td>0.015</td><td>0.3</td><td>2.2</td><td>0.3</td></tr></table>							C	Si	Mn	P	S	Cr	Ni	Mo	0.06	0.4	1.6	0.015	0.015	0.3	2.2	0.3
C	Si	Mn	P	S	Cr	Ni	Mo																
0.06	0.4	1.6	0.015	0.015	0.3	2.2	0.3																
PROPRIÉTÉS MÉCANIQUES	<table><tr><th rowspan="2">Heat Treatment</th><th rowspan="2">R_{P0,2} (MPa)</th><th rowspan="2">R_m (MPa)</th><th rowspan="2">A₅ (%)</th><th colspan="2">Impact Energy (J) ISO-V</th><th rowspan="2">Hardness</th></tr><tr><th>-40°C</th><th>-60°C</th></tr><tr><td>As Welded</td><td>705</td><td>850</td><td>20</td><td>75</td><td>50</td><td>HRc</td></tr></table>							Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	-40°C	-60°C	As Welded	705	850	20	75	50	HRc
Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness																	
				-40°C	-60°C																		
As Welded	705	850	20	75	50	HRc																	
ETUVAGE	Not required																						
GAS ACC. EN ISO 14175	M21																						



CEWELD AA R690

AA R690 1,2MM

Packaging	KG/unit	EanCode
BS-300	16	8720663423733
D-200	20 (4x5)	8720663423726