



CEWELD CuSiMn Tig

TYPE Copper-Silicon-Manganese alloy for TIG welding

APPLICATIONS Welding CuMn, CuSiMn, pure copper and copper alloys.

PROPRIÉTÉS Good flowing alloy with less pores and excellent de-oxidation properties.

CLASSIFICATION EN ISO 24373: Cu 1898A / CuSn1MnSi

CONVIENT POUR Welding thin steel plates and or galvanized plates in the car industry and also for cladding CuMn, CuSiMn and CuZn alloys. Suitable for cladding cast iron and un- and low alloyed steels.

AGRÉMENTS

POSITIONS DE SOUDAGE



**ANALYSE CHIMIQUE
TYPIQUE DU MÉTAL
D'APPORT (%)**

Si	Mn	P	Fe	Cu	Pb	Sn
0.2	0.2	0.01	0.02	Rem.	0.005	0.8

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
As Welded	250			HRc

ETUVAGE Not required

GAS ACC. EN ISO 14175 I1



CEWELD CuSiMn Tig

CUSIMN TIG 2,4 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663408440

CUSIMN TIG 3,2 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663408457