


CEWELD Ni-Rod 44

TYPE	Solid Nickel-Iron-Manganese welding wire for cast iron		
TOEPASSINGEN	Ductile, gray and malleable Cast Iron and cast steel repairs, rebuilding wornout parts and also suitable for joining steel to cast Iron.		
EIGENSCHAPPEN	Excellent wetting properties that enable this welding wire to weld with high welding speed due to the high manganese content. Thermal expansion is very low (close to NILO) and the weld deposit is extreme crack resistant.		
CLASSIFICATIE	AWS EN ISO	A 5.15: E NiFeMn-CI 1071: NiFeMn-CI	
GESCHIKT VOOR	Grey cast iron, malleable, nodular : NF A 32-101 : FGL 150, 200, 250, 300, 350, 400. NF A 32-201 : FGS 370-17, 400-12, 500-7, 600-3, 700-2. NF A 32-702 : MN 350-10, 380-18, 450-6, 350-4, 650-3. DIN 1691 : CG-14, 18, 25, 30. DIN 1693 : GGG-40, 50, 60, 70. DIN 1692 : GTS-35, 45, 55, 65, 70.		

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Si	Mn	Ni	Al	Fe
0.25	0.08	12	42	0.3	Rem.

MECHANISCHE WAARDEN

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded		690	35	190 HB

HERDROGEN

Not required

GAS ACC. EN ISO 14175

I1