



CEWELD L-CuPSn7

TYPE	Copper Phosphorus Brazing Alloy	
TOEPASSINGEN	Suitable for gap brazing of copper and copper alloys. Joint-brazing at working temperatures between -20°C and +150°C. Do not use in sulphurous environment and on Fe- and Ni-alloys.	
EIGENSCHAPPEN	Filler metal with good flowing properties and capillarity. Colour very similar to brass. Soldering seam can be easily electroplated. Self pickling on copper to copper joints.	
CLASSIFICATIE	AWS	A 5.8: BCuP-2
GESCHIKT VOOR	Brazing of copper, copper alloys, brass,	
GOEDKEURINGEN		
LASPOSITIES		
MECHANISCHE WAARDEN		
HERDROGEN	Not required	
GAS ACC. EN ISO 14175		